



Description	<p>T36-P. 36μ gloss clear 3 year easy clean polyester, permanent UV laminating adhesive, 140gsm PE liner.</p> <p>T-Series' gloss clear polyester with a low surface energy coating and a clear medium tack permanent adhesive on a stay-flat PE liner. Primarily for temporary covering of work surfaces. The easy clean top coating allows bacteria, dirt etc. to be cleaned off thoroughly, quickly and repeatedly. Particularly suitable to protect textures surfaces that are very difficult to clean.</p>				
Key Features	<p>Gloss clear easy clean top coated PET</p> <p>Rigid polyester base does not shrink.</p> <p>Available up to 1530mm wide.</p> <p>Laminating adhesive is suitable for most common work surfaces.</p> <p>Laminating adhesive is suitable for all digital inks including UV.</p> <p>Splice free rolls.</p>				
Conversion	<p>Primarily for laminating.</p> <p>PET film is not conformable.</p>				
Precaution	<p>With polyester films there is always a risk of leaving adhesive during removal at the end of life.</p> <p>For application to flat surfaces only.</p>				
Application	<p>Wet application is highly recommended.</p>				
Compliance	<p>REACH and RoHS compliant</p>				
Fire Certification	<p>Not Applicable</p>				
Face Material	<p>Clear top coated Polyester</p>				
Face Thickness	<p>36μ thick</p>				
Adhesive	<p>Permanent clear UV polyacrylate</p>				
Adhesive weight	<p>Nominal 30gsm</p>				
Perceived Tack	<p>Medium Tack Permanent</p>				
Liner	<p>140gsm PE liner</p>				
Dimensional stability	<p>N/A</p>				
Conformability	<p>1D Flat-sided</p>				
Optimal application temp	<p>+15 to 25°C</p>				
Min application temp	<p>+10°C</p>				
Max application temp	<p>+30°C</p>				
Intermittent service temp	<p>-30 to 100°C</p>				
Shelf-life	<p>2 year</p>				
Adhesive Data (Nominal)	180° Peel Adhesion N/25mm				
		Stainless Steel	Glass	Polypropylene	MDF
	20 min	13	17	1	3
	24 hour	15	19	2	5
	1 week	19	24	2	6
Chemical Resistance	<p>The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.</p>				
Outdoor Durability	<p>3 year unprinted Zone 1 (Northern Europe, North America) vertical exposure</p> <p>1-2 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure</p> <p>1 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure</p>				
Important	<p>The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to www.nu-coat.com/testmethods. Nu-Coat Limited will not be liable for any indirect or consequential loss.</p>				